

**BOLSOL 260KY**

Suda Çözünmeyen Korozyon Önleyici

Water-Insoluble Corrosion Inhibitor

**1. Fiziksel ve Kimyasal Özellikler**

<b>Fiziksel durum</b>	Sıvı
<b>Renk</b>	Berrak-Kızıl kahve
<b>Koku</b>	Karakteristik
<b>pH</b>	Uygulanamaz
<b>Yoğunluk (15°C) (g/ml)</b>	0,80 ± 0,05
<b>Parlama Noktası(°C)</b>	<60
<b>Viskozite (40°C)(cSt)</b>	1-2
<b>Yağda Çözünürlük</b>	Çözünür
<b>Suda Çözünürlük</b>	Çözünmez

**2. Açıklama**

- Metal yüzeylerde(demir, alüminyum, pirinç vs.) mükemmel pas koruma sağlar.
- Hidrofobik (su itici) özelliği sayesinde ürünün kullanım ömrü uzundur.
- Üzerinde su veya soğutma sıvısı bulunan boruların, profillerin ve küçük parçaların pastan korunmasında, ara depolanmasında başarı ile kullanılır.
- Ürün metal yüzeye uygulandığında, metal yüzeyinde ince kuru film tabakası oluşturur.
- Sundurma altında metal yüzeyinde 3 ay, kapalı alanda 6 ay pas koruma sağlar.

**3. Uygulama**

Metal yüzeyine tatbiki 3 şekilde olabilir;

- 1- Daldırma
- 2- Püskürtme
- 3- Fırça ile sürme

**4. Raf Ömrü**

Orijinal ambalajında, 5°C ile 25°C arasında depolanmalıdır. Raf ömrü 24 aydır.

**5. Paketleme**

20L'lik, 30L'lik, 60L'lik plastik bidon, 200L'lik sac varil veya 1000L'lik IBC.

**1. Physical And Chemical Properties**

<b>Physical state</b>	Liquid
<b>Color</b>	Clear-Reddish brown
<b>Odor</b>	Characteristic
<b>pH</b>	Not applicable
<b>Density (15°C) (g/ml)</b>	0,80 ± 0,05
<b>Flash Point(°C)</b>	<60
<b>Viscosity(40°C)(cSt)</b>	1-2
<b>Solubility in oil</b>	Soluble
<b>Solubility in water</b>	Insoluble

**2. Explanation**

- It provides excellent anti-corrosive feature on metal surfaces.
- Via hydrofobic feature, the lifetime of the product is long.
- BOLSOL 260 KY is used successfully in the interim storage of pipes, profiles and small metals with water or coolant on them.
- When BOLSOL 260KY is used 100% concentrate, it forms a thin dry film layer that prevents corrosion 3 months under shelter on metal surface, 6 months in closed area.

**3. Application**

It can be applicated in 3 different ways:

- 1- Dipping
- 2- Spraying
- 3- Brushing

**4. Shelf Life**

It should be stored between 5°C and 25°C in its original package. Shelf life is 24 months.

**5. Packaging**

20L, 30L, 60L of plastic drums, 200L of barrels or 1000L of IBC.

**BOSTANCI KİMYA SAN. VE TİC. LTD. ŞTİ**İstanbul Tuzla Kimya Sanayicileri OSB Melek Aras Bul.  
Analitik Cad. No: 3 Tuzla / İSTANBUL☎ : +90 216 593 05 67  
☎ : +90 216 593 05 69✉ info@bostancikimya.com.tr  
🌐 www.bostancikimya.com.tr